NANO EXPRESS

Open Access

A facile approach to a silver conductive ink with high performance for macroelectronics

Yu Tao^{1*}, Yuxiao Tao¹, Biaobing Wang¹, Liuyang Wang¹ and Yanlong Tai^{2*}

Abstract

An unusual kind of transparent and high-efficiency organic silver conductive ink (OSC ink) was synthesized with silver acetate as silver carrier, ethanolamine as additive, and different kinds of aldehyde-based materials as reduction agents and was characterized by using a thermogravimetric analyzer, X-ray diffraction, a scanning electron microscope, and a four-point probe. The results show that different reduction agents all have an important influence on the conductive properties of the ink through a series of complex chemical reactions, and especially when formic acid or dimethylformamide was used as the reduction agent and sintered at 120°C for 30 s, the resistivity can be lowered to 6 to 9 $\mu\Omega$ cm. Furthermore, formula mechanism, conductive properties, temperature, and dynamic fatigue properties were investigated systematically, and the feasibility of the OSC ink was also verified through the preparation of an antenna pattern.

Keywords: Organic silver conductive ink (OSC ink), Conductive pattern, Formula mechanism, Antenna pattern

Background

Most research efforts in macroelectronics have opened the door for the manufacture of lightweight, flexible, cost-effective electronic devices that are beyond the conventional silicon-based devices, including flexible displays [1], flexible and conformal antenna arrays [2], electronic solar cell arrays [3], radio-frequency identification tags [4], flexible batteries [5], electronic circuits fabricated in clothing [6], and biomedical devices [7]. Usually, most of them require electrical contacts.

Up to now, various materials such as conjugated polymers, graphene, carbon nanotubes, and metals have been used for the preparation of electrodes and conductive patterns using solution processing methods [8-11]. Specifically, metal nanoparticle inks have attracted more and more attention due to their high conductivity and thermal stability after having been sintered [12-14].

However, metallic nanoparticle inks often require high annealing temperatures (>150°C) to decompose stabilizing agents and other polymeric additives that inhibit electrical conductivity, with the high annealing

* Correspondence: taoyu@cczu.edu.cn; yltai@ucdavis.edu

temperature limiting the choice of substrate. Besides, they still cannot completely avoid the condensation and agglomeration of nanoparticles, especially after longterm storage. The agglomerated particles may damage the equipment and influence the printing quality. During preparation, a high-speed centrifuge or vacuum dryer must be used to take nanometal particles out, so these inks cannot be produced on a large scale. All of these will cause a higher production cost [15-18].

There is no surprise to the fact that organic silver conductive ink (OSC ink) has received increasing attention as a potentially much lower cost alternative [19-21]. This kind of ink mainly consists of a silver carrier, weak reduction agent, solvent, and additives, and a continuous conductive silver track can be fabricated during the sintering process. This strategy can compensate for the lack of conductive metal nanoink and thus becomes the development direction of conductive ink for macroelectronics [22-25].

In our previous research, the relationship between different kinds of amines and ink properties was investigated systematically. The addition of different amines not only increased the solid content of the conductive ink but also decreased the sintering temperature by complexation [26-28].

Here, based on the previous results, the formula of the conductive ink will be further optimized using silver



© 2013 Tao et al.; licensee Springer. This is an Open Access article distributed under the terms of the Creative Commons Attribution License (http://creativecommons.org/licenses/by/2.0), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

¹School of Materials Science and Engineering, Changzhou University, Changzhou 201326, People's Republic of China

²Department of Biomedical Engineering, University of California Davis, Davis, CA 95616, USA

acetate as silver carrier, ethanolamine as additive, and different kinds of organic aldehyde as reduction agents, such as ethylene glycol, acetaldehyde, formic acid, dimethylformamide, and glucose. Furthermore, the formula mechanism, conductive properties, temperature, dynamic fatigue properties, and feasibility verification of the OSC ink through the preparation of an antenna pattern were also investigated systematically [29-31].

Methods

Materials

Silver acetate was obtained from Shanghai Lingfeng Chemical Reagent Co., Ltd. (Shanghai, China). Polydimethylsiloxane (PDMS) including base and curing agents was obtained from Dow Corning Co. (Midland, MI, USA; SYLGARD 184 silicone elastomer). Polyester film (0.1 \pm 0.02 mm) came from Shanghai Weifen Industry Co., Ltd (Shanghai, China). Ethylene glycol, acetaldehyde, formic acid, dimethylformamide, glucose, ethyl alcohol, and other solvents were of analytical grade and used without further purification. Deionized water was used in all experimental processes.

Synthesis of OSC ink

For the preparation of conductive ink (1 g), silver acetate (0.32 g; which means if all silver ions are reduced to elemental silver, the content of elemental silver is 20 wt.%) and ethanolamine (0.2 g) were added to ethanol (0.13 g) and different reduction agents (0.35 g; ethylene glycol, acetaldehyde, formic acid, dimethylformamide, or glucose, etc.) under vigorous stirring until a transparent solution was obtained.

Preparation of antenna pattern

For the preparation of the PDMS pattern as template, polyethylene terephthalate (PET) was adhered to a sheet glass using both side tapes, and 3-g PDMS (base/curing agent is 15/1) was dropped on the center of the PET film. Then, after spin coating (800 rpm), baking at 80°C for 3 h, and laser etching, the desired PDMS pattern as template can be fabricated with the conductive track (a thickness of 200 μ m and a width of 200 μ m).

For the preparation of the antenna pattern, the synthesized OSC ink was dropped into the trench of the PDMS template track using a syringe, and the ink will flow to all of the track spontaneously until full; then, it will be sintered at 120°C for 30 s. Finally, the PDMS template can be peeled off easily by forceps, and the desired antenna pattern was achieved [32].

Instrumentation

OSC ink was characterized by using a Ubbelohde viscometer (CN60M, Zxyd Technology Co., Ltd., Beijing, China); a surface tension instrument (A101, Kino Industry Co., Ltd, New York, USA); X-ray diffraction (XRD; max 2550 PC, Rigaku-D, Rigaku Corporation, Tokyo, Japan) using Cu Kα radiation; scanning electron microscopy (SEM; S-360, Cambridge Instruments Ltd., Cambridge, England) operated at 10 kV; thermogravimetric analysis (TGA; QS-500, TA Instruments Inc., New Castle, DE, USA) with a heating rate of 5°C·min⁻¹ in a nitrogen atmosphere; a fourpoint probe equipped with a semiconductor characterization system (BD-90, Shanghai Power Tool Institute, Shanghai, China); a memory hicorder (8870-20, HIOKI, Nagano, Japan) with a heating device from room temperature to 120°C, a steady current mechanism (10 mA), and an amplifier (×100); and a dynamic fatigue tester (built in the lab) with steady current mechanism (10 mA). The antenna pattern was investigated using a Uscan explorer with 3D profilometer system (D46047, Nanofocus, Oberhausen, Germany).

Results and discussion

Formula mechanism

Compared with nanosilver conductive ink, the synthesized silver organic ink is transparent and clear without any visible particles. During the preparation process, this kind of conductive ink was mainly composed of a silver carrier, weak reduction agent, solvent, and additives. At the room temperature, it was very stable and can be kept for at least 1 month. Once it was heated, the complex chemical reaction occurred between the various components. Generally speaking, the sintering process can be divided into four stages: firstly, from simple silver ion to silver ion complex, then to silver oxide, and finally to elemental silver. Meanwhile, the color also changes from colorless to faint yellowish brown, to black, and to metallic luster. The details can be seen from Figure 1 directly.

In this formula, silver acetate was chosen as silver carrier, which can control the reaction rate effectively by adjusting the concentration of the silver ion in the mixing solvent because of its worse solubility. Ethanolamine was used to increase the silver content of the conductive ink to guarantee the conductivity and further to decrease the sintering temperature.

Different aldehyde-based materials were chosen as weaker reduction agents, which have been discussed in detail as shown in Figure 2. Generally speaking, such materials can be divided into two types: one for itself with the aldehyde group, such as acetaldehyde, formic acid, dimethylformamide, and glucose; another for itself without the aldehyde group, but after heating, the aldehyde group can appear, such as ethylene glycol which can change to acetaldehyde at a high temperature and glycolic acid which can be decomposed into formaldehyde, carbon monoxide, and water at 100°C. The results



show that reduction agent plays an important role on the properties of the conductive ink. Usually, a stronger reduction agent will bring in the instability of the ink, leading to the precipitation of silver particles and lower conductivity. Conversely, a weak reduction agent will result in a higher sintering temperature. It can be inferred that a suitable reduction agent is very important to get lower resistivity. From Figure 2, at the sintering temperature of 120°C for 1 h, the resisitivity of the silver thin film with different formulas should be very stable. It can be seen that formic acid and dimethylformamide show lower resistivity of about 6 to 8 $\mu\Omega$ -cm and 7 to 9 $\mu\Omega$ -cm, respectively. In view of the formula stability, in the following research, dimethylformamide was chosen as the reduction agent.

OSC ink properties

For further investigation of the OSC ink, dimethylformamide was used as reduction agent in the formula. The viscosity and surface tension were adjusted to 13.8 mPa·s and 36.9 mN/m (20°C), which can totally fulfill the requirement of ink-jet printing, as shown in the inset of Figure 3a.



The thermal properties of the prepared OSC ink were investigated by TGA with a heating rate of 5°C/min, as depicted in Figure 3a. It can be seen that there exists an evident mass-decreasing area, from 80°C to 160°C, which is related to the evaporation of organic materials; finally, 20.3 wt.% of the mass remains, which indicates that the ink contains 20.3 wt.% silver and agrees well with the calculated value (20 wt.%). If several drops of ammonia were added, the solid content can be further increased to 28 wt.% at most because of its stronger coordination ability than ethanolamine. However, more ammonia will cause the instability of the conductive ink due to its volatilization.

The conductive properties of the prepared OSC ink were investigated using different sintering temperatures (90°C, 120°C, 150°C) for different durations of time (from 0 to 60 min), which also can be explained by percolation theory, as shown in Figure 3b. During the sintering process, initially, there are only silver acetate and silver oxide, without any elemental silver, so there is no conductivity. Then, almost all of the silver oxide was reduced to elemental silver at the same time, indicating that a continuous conductive track has been fabricated and showing metallic luster and high conductivity. Especially, based on the present formula of the ink, when the sintering temperature is 120°C for 30 s, the resistivity can drop to 7 to 9 $\mu\Omega$ ·cm.

Figure 3c shows an XRD pattern of the silver ink after sintering, and all diffraction peaks could be indexed to the face-centered cubic phase of silver. The lattice constant calculated from this XRD pattern was 4.098, which was very close to the reported data (a = 4.0862, JCPDS file no. 04–0783). The inset is the surface morphology of the conductive ink after sintering, and more information also can be seen from Figure 3d.

Temperature and dynamic fatigue properties

To verify the applicability of this approach in macroelectronics, the correlations between resistivity and temperature, and dynamic fatigue of the conductive silver







line were investigated systematically, which were shown in Figure 4.

From Figure 4a,b, a set of equipment including a heating device from room temperature to 120°C, steady current mechanism (10 mA), amplifier (×100), memory hicorder (HIOKI, 8870-20), etc. were assembled together, aiming at monitoring the changes of the resistivity of the conductive silver line during the heating and cooling processes. It can be obtained that between 20°C and 100°C, the largest variable quantity of the resistivity is just about 0.28 Ω . After linear fitting, the slopes of the heating curve and the cooling curve, which can be called temperature coefficient of resistance (TCR), approximately have the same slope (kh = kc = $0.0007 \text{ aR/}^{\circ}\text{C}^{-1}$), indicating the good thermal stability of the conductive silver line. The TCR is a little different compared with the TCR of bulk silver (0.0038 $aR/^{\circ}C^{-1}$). This phenomenon is mainly caused by the complex microstructure of the silver thin film which will bring more barriers during the electron-transfer process. Moreover, it also can be seen that though the heating curve and cooling curve have the same TCR, the cooling curve is always below the heating curve. This is mainly because the natural cooling process (about 28 min) needs more time than the heating process (15 min).

From Figure 4c, a bending tester was used to study the dynamic fatigue of the PET-based conductive silver line. During the test, the conductive line makes a periodic bending movement from I to V, and every period needs 2 s. The details also can be seen from the set in Figure 3b. It is very interesting to find that the resistivity of the conductive silver lines also increases with the increase of the bending angle. From I to III, the resistivity increases from 5.2 to 5.76 Ω . It can be explained that when bending, the silver thin film was stretched and became thin, especially on the top point of the conductive line, so the stack density and conductivity decreased. From III to V, the resistivity was back to 5.2 Ω , and after a periodic movement like this for 1,000 times, the resistivity did not significantly increase due to the good ductility of the metal silver. Generally speaking, compared with other printing technologies, this method also shows good adhesion between the silver thin film and PET, showing good results.

Preparation of an antenna pattern

To test the practical applications of the prepared OSC ink here, an antenna pattern (11 mm \times 12 mm) was designed and fabricated using fit-to-flow or drop method, which also can be seen from Figure 5 directly.

The thin film PDMS pattern with a thickness of 200 μ m, a width of 200 μ m, and a total length of 15.8 cm on the PET substrate was prepared using a laser and used as template. The synthesized OSC ink with blue dye (seen more clearly) was dropped to the center of the template using a syringe (20 μ L per drop). Due to the good wetting and film-forming ability of the ink, it will flow along the template track until it fills the whole track, especially after plasma treatment with oxygen. After sintering at 120°C for 30 s, the continuous conductive track can be fabricated, and the total resistor R_{ab} decreased to 4.6 Ω measured by a multimeter (middle image of Figure 5) with a width of 200 μ m and thickness of 22 μ m according to the surface profile.

Conclusions

In summary, an unusual kind of high-efficiency, transparent organic silver conductive ink (OSC ink) was synthesized with silver acetate as silver carrier, ethanolamine as additive, and different kinds of aldehyde-based materials as reduction agents successfully. The results show that different reduction agents have an important influence on the ink properties through a series of complex chemical reactions, and when formic acid or dimethylformamide was used as the reduction agent and sintered at 120°C for 30 s, the resistivity can be lowered down to 6 to 9 $\mu\Omega$ -cm. It also can be obtained that the fabricated conductive pattern shows good temperature and dynamic fatigue properties. Besides, the feasibility of the synthesized OSC ink was verified through the



Figure 5 Antenna pattern after sintering at 120°C for 30 s and surface profile curves of conductive pattern. The prepared antenna pattern was fabricated using drop or fit-to-flow method.

preparation of an antenna pattern using drop or fit-to-flow method successfully.

Competing interests

The authors declare that they have no competing interests.

Authors' contributions

Y-LT synthesized the organic silver conductive ink and discussed the formula. YT, LW, YT, and BW characterized and investigated the properties of the OSC ink. All authors took part in the writing of the manuscript and approved the final manuscript.

Acknowledgments

This work was supported by the project funded by the Priority Academic Program Development of Jiangsu Higher Education Institutions (PAPD).

Received: 22 March 2013 Accepted: 23 May 2013 Published: 25 June 2013

References

- Chen Y, Au J, Kazlas P, Ritenour A, Gates H, McCreary M: Flexible activematrix electronic ink display. *Nature* 2003, 423:136.
- Bairavasubramanian R, Thompson D, Ponchak GE, Tentzeris MM, Papapolymero-u J: Liquid crystal polymer (LCP): a new organic material for the development of multilayer dual-frequency/dual-polarization flexible antenna arrays. *IEEE Anten Wirel Pr* 2005, 4:22–26.
- Otte K, Makhova L, Braun A, Konovalov I: Flexible Cu(In, Ga) Se2 thin-film solar cells for space application. *Thin Solid Films* 2006, 511:613–622.
- Baeg KJ, Khim D, Kim J, Yang BD, Kang M, Jung SW: High-performance top-gated organic field-effect transistor memory using electrets for monolithic printed flexible NAND flash memory. *Adv Funct Mater* 2012, 22:2915–2926.
- 5. Nishide H, Oyaizu K: Toward flexible batteries. Science 2008, 319:737–738.
- Meng Y, Zhao Y, Hu C, Cheng H, Hu Y, Zhang Z, Shi G, Qu L: All-graphene core-sheath microfibers for all-solid-state, stretchable fibriform supercapacitors and wearable electronic textiles. *Adv Mater* 2013, 25:2326–2331.
- Cha C, Shin SR, Annabi N, Dokmeci MR, Khademhosseini A: Carbon-based nanomaterials: multifunctional materials for biomedical engineering. ACS Nano 2013, 7:2891–2897.
- Wang JZ, Zheng ZH, Li HW, Huck WTS, Sirringhaus H: Dewetting of conducting polymer inkjet droplets on patterned surfaces. Nat Mater 2004, 3:171–176.
- Huang X, Qi X, Boey F, Zhang H: Graphene-based composites. Chem Soc Rev 2012, 41:666–686.
- Mensing JP, Kerdcharoen T, Sriprachuabwong C, Wisitsoraat A, Phokharatkul D, Lomas T: Facile preparation of graphene-metal phthalocyanine hybrid material by electrolytic exfoliation. J Mater Chem 2012, 22:17094–17099.
- 11. Wu L, Li Y, Ong BS: Printed silver ohmic contacts for high-mobility organic thin-film transistors. J Am Chem Soc 2006, **128**:4202–4203.
- Choi CS, Jo YH, Kim MG, Lee HM: Control of chemical kinetics for sub-10 nm Cu nanoparticles to fabricate highly conductive ink below 150°C. Nanotechnology 2012, 23:065601–065609.
- Russo A, Ahn BY, Adams JJ, Duoss EB, Bernhard JT, Lewis JA: Pen-on-paper flexible electronics. Adv Mater 2011, 23:3426–3430.
- 14. Hösel M, Krebs FC: Large-scale roll-to-roll photonic sintering of flexo printed silver nanoparticle electrodes. *J Mater Chem* 2012, 22:15683–15688.
- Kim J, Kang SW, Mun SH, Kang YS: Facile synthesis of copper nanoparticles by ionic liquids and its application to facilitated olefin transport membranes. *Ind Eng Chem Res* 2009, 48:7437–7441.
- Li Y, Wu Y, Ong BS: Facile synthesis of silver nanoparticles useful for fabrication of high-conductivity elements for printed electronics. J Am Chem Soc 2005, 127:3266–3267.
- Hussain I, Graham S, Wang Z, Tan B, Sherrington DC, Rannard SP: Size-controlled synthesis of near-monodisperse gold nanoparticles in the 1–4 nm range using polymeric stabilizers. J Am Chem Soc 2005, 127:16398–16399.
- 18. Chen S, Carroll DL: Silver nanoplates: size control in two dimensions and formation mechanisms. J Phys Chem B 2004, 108:5500–5506.
- Walker SB, Lewis JA: Reactive silver inks for patterning high-conductivity features at mild temperatures. J Am Chem Soc 2012, 134:1419–1421.

- Wu JT, Hsu SLC, Tsai MH, Hwang WS: Direct inkjet printing of silver nitrate/poly(*N*-vinyl-2-pyrrolidone) inks to fabricate silver conductive lines. J Phys Chem C 2010, 114:4659–4662.
- Rickerby J, Simon A, Jeynes C, Morgan TJ, Steinke JHG: 1,1,1,5,5,5-Hexafluoroacetylacetonate copper(I) poly(vinylsiloxane)s as precursors for copper direct-write. *Chem Mater* 2006, 18:2489–2498.
- 22. Wu Y, Li Y, Ong BS: A simple and efficient approach to a printable silver conductor for printed electronics. J Am Chem Soc 2007, **129**:1862–1863.
- Hiraoka M: Ink-jet printing of organic metal electrodes using chargetransfer compounds. *Appl Phys Lett* 2006, 89:173504–173507.
- Gamerith S, Klug A, Scheiber H, Scherf U, Moderegger E, List EJW: Direct ink-jet printing of Ag–Cu nanoparticle and Ag-precursor based electrodes for OFET applications. Adv Funct Mater 2007, 17:3111–3118.
- Moonen PF, Yakimets I, Huskens J: Fabrication of transistors on flexible substrates: from mass-printing to high-resolution alternative lithography strategies. Adv Mater 2012, 24:5526–5541.
- Chang Y, Wang DY, Tai YL, Yang ZG: Preparation, characterization and reaction mechanism of a novel silver-organic conductive ink. J Mater Chem 2012, 22:25296–25301.
- 27. Li Y, Sun H, Chu H: Controlled preparation of inorganic nanostructures on substrates by dip-pen nanolithography. *Chem Asian J* 2010, **5**:980–990.
- Tai YL, Yang ZG, Li ZD: A promising approach to conductive patterns with high efficiency for flexible electronics. *Appl Surf Sci* 2011, 257:7096–7100.
- Tai YL, Yang ZG: Fabrication of paper-based conductive patterns for flexible electronics by direct-writing. J Mater Chem 2011, 21:5938–5943.
- Dearden AL, Smith PJ, Shin DY, Reis N, Derby B, O'Brien P: A low curing temperature silver ink for use in ink-jet printing and subsequent production of conductive tracks. *Macromol Rapid Commun* 2005, 26:315–318.
- Perelaer J, Smith PJ, Mager D, Soltman D, Volkman SK, Subramanian V, Korvinkdf JG, Schubert US: Printed electronics: the challenges involved in printing devices, interconnects, and contacts based on inorganic materials. J Mater Chem 2010, 20:8446–8453.
- Tao Y, Tao YX, Wang L, Wang B, Yang ZG, Tai YL: High-reproducibility, flexible conductive patterns fabricated with silver nanowire by drop or fit-to-flow method. *Nanoscale Res Lett* 2013, 8:147–152.

doi:10.1186/1556-276X-8-296

Cite this article as: Tao *et al.*: A facile approach to a silver conductive ink with high performance for macroelectronics. *Nanoscale Research Letters* 2013 **8**:296.

Submit your manuscript to a SpringerOpen[®] journal and benefit from:

- Convenient online submission
- Rigorous peer review
- Immediate publication on acceptance
- Open access: articles freely available online
- ► High visibility within the field
- Retaining the copyright to your article

Submit your next manuscript at > springeropen.com